

MATERIAL DATA SHEET

Material type: Alumina

AO476T

Properties of Microstructure

| | | | |
|------------------|------------|-------------------|------|
| Alumina Content | | % | 96 |
| Density | JIS R 1634 | g/cm ³ | 3.78 |
| Water Absorption | | % | 0 |
| Mean Grain Size | | µm | - |

Mechanical Properties

| | | | |
|-----------------------|------------|----------------------|------|
| Vickers Hardness | JIS R 1610 | GPa | 13.9 |
| Compressive strength | JIS R 1608 | MPa | - |
| Flexural strength | JIS R 1601 | MPa | 380 |
| Modulus of Elasticity | JIS R 1602 | GPa | 340 |
| Poisson's ratio | JIS R 1602 | | |
| Fracture toughness | JIS R 1607 | MPa·m ^{1/2} | - |

Thermal Properties

| | | | |
|---|------------|---------------------|-----|
| Specific Heat 20°C | JIS R 1611 | J/gK | |
| Thermal Conductivity | JIS R 1611 | W/mK | 26 |
| Expansion coefficient 40-400°C | JIS R 1618 | 10 ⁻⁶ /K | 7.0 |
| Expansion coefficient 40-800°C | JIS R 1618 | 10 ⁻⁶ /K | |
| Thermal Shock Temperature Difference (in water) | JIS R 1648 | °C | |

Electrical Properties

| | | | |
|-------------------------------|------------|------------------|-------------------|
| Dielectric strength | JIS C 2141 | kV/mm | 15 |
| Specific Resistance 20°C | JIS C 2141 | Ω·cm | >10 ¹⁴ |
| Specific Resistance 300°C | JIS C 2141 | Ω·cm | |
| Specific Resistance 500°C | JIS C 2141 | Ω·cm | |
| Dielectric constant (1 MHz) | JIS C 2141 | | 9.6 |
| Dielectric Loss Angle (1 MHz) | JIS C 2141 | 10 ⁻⁴ | 3 |
| Typical Colour | | | white |

The values are typical material properties and may vary according to products configuration and manufacturing process.